

Densurf HR 900

Silicone Resin

Content Publish Date: 21.05.2026
Content Revision Date: 21.05.2026
Content Revision No : 001

PRODUCT DESCRIPTION

Densurf HR 900 is a high molecular weight phenyl-polysiloxane resin that can be cured under the specified temperature.

APPLICATIONS & KEY FEATURES

It provides thermal resistance up to the 800 - 850 °C when it is formulated correctly.
It is used for the heat and the corrosion resistant solvent-based coatings.

The main application areas of the Densurf HR 900 are:

- Heat Resistant Applications
- General Industrial Paints

SOLUBILITY

Water	Ethanol
	
N-Butyl Acetate	Isobutanol
	
Xylene	Methoxy Propyl Acetate
	
	
Soluble	Not Soluble

**Detailed knowledge about the suitable diluents can be asked to the technical support team. The provided diluents are the references according to the most common application areas.

STORAGE

Please store the unopened packaging between 5°C - 35°C.
The shelf life is at least 12 months for unopened packagings.
Close the packaging cap tightly after use.

WARNING! Keep away from the acids, the heat and the moisture.

SPECIAL NOTES

Densurf HR 900 provides an excellent hydrophobicity and the corrosion-protection.

It has good balance of the exibility, the stiffness, the heat resistance and the curing temperature.

TECHNICAL PROPERTIES

- Chemical Structure: Phenyl-polysiloxane resin
- Appearance: Transperent/hazy liquid
- Density (20°C): 1,15 ± 0,02 g/mL
- Solid Content (10 mins., 160°C): 50,00 ± 2,00 %
- Solvent: Xylene

SYSTEM

Long Oil Alkyd Resins



Short Oil Alkyd Resins



Solvent-Based Epoxy Resins



Polyester Resins



Thermoplastic Acrylic



Acrylic Polyol Resins



Suitable

Not Suitable

**Detailed knowledge about the compatible systems can be asked to technical support team. The provided systems are the references according to the most common application areas.

DOSAGE

Recommended amount: 30.00 - 50.00 % (by weight as supplied based on the total formulation)

Note: Amounts mentioned above are just a recommendation.
Please make laboratory tests to specify the optimum amounts.

PROCESS RECOMMENDATION

It can be cold-blended with the suitable organic resins.
Surface pre-treatment is needed.

It completes its touch-free dry within the 1 hour after the application.

It needs to heat under the specified heat and the curing time 250°C / 30 min.